12AL100N **12ALZ100N**

AMARON QUANTATM

The industrial segment SMF-

is built to perform.

applications

RadgridTM

VRLA (Valve Regulated Lead Acid) battery for UPS applications

In short, the lifeline to your UPS

AMARON QUANTA ™ is a product of fail- safe, fool-proof battery technology, produced and tested in our premier manufacturing facility.

Built to the highest technical competence in its class, the

QUANTA is an example of Amara Raja's commitment to bringing the best of technology to your table

It features several firsts for the battery industry like the unique

TERMINAL LAYOUT


Ø23.1




Specification

Nominal Voltage		12V
Rated Capacity		100Ah / C ₂₀ Hr / 1.75VPC / 27°C
	Length	393 mm (15.47 in.)
Dimensions (±2mm)	Width	173 mm (6.81 in.)
	Total Height	221 mm (8.70 in.)
Weight (±5%)		31.5 Kg (69.45 lbs)
Terminal Type		M8 x 25mm Copper terminal
	93.10 Ah	(10hr, 9.31 A, 10.5 V/battery)
Capacity @ 27°C	85.75Ah	(5hr, 17.15 A, 10.2 V/battery)
	63.70 Ah	(1hr, 63.70 A, 9.6V /battery)
_	40°C (104°F)	110%
Capacity affected	27°C (80.6°F)	100%
(Temperature at C20 hr rate)	0°C (32°F)	80%
	-15°C (5°F)	60%
Case Material	Standard	PPCP (12AL100N)
Case Material	FR Version	UL 94-V0 (12ALZ100N)
Internal Resistance (IR)	Approx. 5.60 mΩ	for a fully charged battery (27°C)
Short Circuit Current (As per IEC)		2220 A
Operating Temp. range	-20°C to +60°	C (50 to 60°C for shorter duration)
Nominal Operating Temp. range		27°C ± 3°C
Standby use (27°C)	Charging Voltage	13.5 V/battery
	Charging Current	Max. 25% of rated capacity
	Temp. Compensation	± 18mV/battery/°C
	Charging Voltage	13.8 V/battery
Cyclic use (27°C)	Charging Current	Max. 25% of rated capacity
	Temp. Compensation	± 30mV/battery/°C







				Temp. Compensation ± 50m v/battery/ C			/ C				
Self-Disc	Self-Discharge < 4% per month at 27°C										
Constant Power Discharge Rating (Watts Per Battery) @ 27°C *											
ECV/ Time	10min	15min	20min	30min	60min	2hrs	3hrs	5hrs	8hrs	10hrs	20hrs
1.60	2416	2010	1500	1209	750	453	331.0	222.0	151.0	122.0	62.0
1.65	2362	1947	1438	1183	734	447	322.0	217.0	148.0	121.0	61.5
1.70	2308	1883	1376	1157	717	440	313.0	212.0	145.0	120.0	61.0
1.75	2254	1820	1364	1131	700	433	304.0	207.0	142.0	119.0	60.5
1.00	2200	1756	1252	1105	602	126	205.0	202.0	120.0	110.0	60.0

Constant Current Discharge Rating (Amperes) @ 27°C *											
ECV/ Time	10min	15min	20 min	30min	60 min	2 hrs	3 hrs	5 hrs	8hrs	10 hrs	20 hrs
1.60	217.39	172.41	140.80	102.04	63.69	39.39	26.92	18.53	11.49	9.72	5.36
1.65	210.74	166.85	136.10	100.52	63.09	37.79	26.10	17.84	11.24	9.60	5.22
1.70	204.10	161.30	131.50	99.00	62.50	36.19	25.29	17.15	10.99	9.49	5.09
1.75	200.00	158.70	129.80	98.00	61.00	35.71	25.25	17.09	10.93	9.31	5.00
1.80	196.10	153.80	126.50	96.20	59.50	35.46	25.13	16.95	10.87	9.26	4.97

All dimensions are in mm

- Note:

 1. The above data are average values per battery and can be obtained within five charge/discharge cycle

 2. A tolerance of ±5% is applicable for the above constant power discharge and constant current discharge values.

 3. Recommended to follow IEEE -485 Standard for Battery sizing (In terms of Aging Margin, Design Margin) for Optimal Performance & Life.

 4. Considerable Voltage drop across cables, if any shall be considering during battery sizing.





CAUTION

- Avoid short circuit
- Don't charge in a sealed container







Performance

A clutch of design features ensures that AMARON QUANTA $^{\mathrm{TM}}$

batteries perform predictably and reliably every time

- Proven AGM technology that ensures maintenance free characteristics
- A unique heavy duty corrosion-resistant alloy for positive grids to increase cyclic life in tropical
- ✓ RadgridTM profile provides lower internal resistance and superior high-discharge performance
- ✓ Instacharge [™] a patented paste recipe for excellent charge acceptance
- ✓ Low self-discharge rates for extended storage periods
- ✓ Design Float life of upto 10 years
- ✓ Clean and Sleek looks


Compliance


- ✓ JIS C 8702 Certified
- ✓ UL (UL-1989) & CE Certified
- ✓ Complies to IEC61056 & EUROBAT
- ✓ Complies to IS 16220
- ✓ Manufactured in ISO 9001, ISO 14001, ISO 45001:2018 certified facilities

Applications


- ✓ Data Centers
- ✓ Banks & Financial Markets
- ✓ Network Operations Centers
- ✓ Industrial Process Control Facilities
- ✓ Safety, Surveillance & Security Systems
- ✓ Semiconductor Manufacturing
- ✓ Power Generation Plants
- ✓ Hospital & Testing laboratories

Discharge Characteristics






Temperature Effect on Capacity



Float Service Life vs. Temperature



AMARA RAJA ENERGY & MOBILITY LIMITED

(Formerly Known as Amara Raja Batteries Limited)

• Corporate Operations Office:

 $Terminal~A,~1-18/1/AMR/NR,~Nanakramguda,~Gachibowli,~Hyderabad-500032,~India,~\underline{E-Mail:~mktg@amararaja.com~www.amararajaeandm.com}$

Registered Office & Manufacturing Facility-1:

UNIT-I,Karakambadi - 517520, Tirupati, Andhra Pradesh, India, TEL: +91-877-2265000, FAX: +91-877-2285600

Manufacturing Facility-2

UNIT-II, Nunegundlapalle, Bangarupalyam, Chittoor - 517416. Andhra Pradesh, India

ARE&M/IAE/AQ/100Ah; Oct'2023, Rev-01

AMARA RAJA